

TECHNICAL DATA SHEET

SEALECTION® 500 is a two component, open cell, spray applied, semi-rigid polyurethane foam system. This product is a fully water blown foam system with a low in-place density with excellent adhesion to various substrates and to itself. SEALECTION® 500 incorporates the single phase solution technology developed by Demilec (USA) LLC for excellent shelf life and consistent processing. SEALECTION® 500 complies with the intent of the International Code Council's residential and commercial building codes for spray polyurethane foam plastic insulation. SEALECTION® 500 has been approved by the EcoLogoSM (formerly Environmental Choice) Program of Canada and is an NAHB Green Approved Product. SEALECTION® 500 meets the USDA guidelines for incidental food contact.

Physical Properties			
ASTM D 1622	Density	0.45 – 0.5 lb/ft ³	7.2 – 8 Kg/m ³
ASTM C 518	Aged thermal resistance (R-Value @ 1 inch)	3.81 ft ² h°F/BTU	0.67 Km ² /W
ASTM E 283	Air leakage (air impermeable IAW 2006, 2009 & 2012 IRC, IBC & IECC requirements)		
	Air permeance @ 75 Pa @ 3.5" Sustained wind load for 60 minutes @ 1000 Pa (90 mph wind) Gust wind load test @ 3000 Pa (160 mph wind)	0.001 L/sm ² No damage No damage	
ASTM E 2178	Air permeance @ 50 Pa @ 3.5"	0.001 L/sm ²	
	Air permeance @ 100 Pa @ 3.5"	0.003 L/sm ²	
	Air permeance @ 300 Pa @ 3.5"	0.008 L/sm ²	
ASTM E 96	Water vapor permeance @ 3.5"	6.33 perms	362 ng/Pa•s•m ²
	Water vapor permeance @ 5.5"	4.03 perms	231 ng/Pa•s•m ²
	Water vapor permeance @ 7"	3.17 perms	181 ng/Pa•s•m ²
	Water vapor permeance @ 10" (Class III vapor retarder at normal installed thicknesses)	2.20 perms	126 ng/Pa•s•m ²
ASTM E 413	Sound Transmission Class (STC) (See website for assembly specs)	49 – 51	
ASTM C 423	Noise Reduction Coefficient (NRC)	75	
CAN/ULC-S774-09	VOC emissions standard	24 hour occupancy time – 2 hour ventilation period before PPE is no longer required	
ASTM D 1621	Compressive strength	0.7 psi	4.8 kPa
ASTM D 1623	Tensile strength	5.6 psi	38.6 kPa

Fire Test Results		
ASTM E 84	Surface burning characteristics, 6" thick Flame spread index Smoke developed	Class I 21 216
NFPA 286	Ignition barrier – Compliant with the 2006, 2009 & 2012 IBC and IRC, and ICC-ES AC-377 Appendix X, for use in attics and crawl spaces with: BLAZELOK™ IB4 at 3 mils dry film thickness, 5 mils wet film thickness, or Adek Firegard at 10 mils dry film thickness, 16 mils wet film thickness, or No Burn Plus XD at 4 mils dry film thickness	Pass
NFPA 286	Thermal barrier – Compliant with the 2006, 2009 & 2012 IBC and IRC, as an interior finish without a 15 minute thermal barrier when BLAZELOK™ TB is applied at 14 mils dry film thickness, 25 mils wet film thickness.	Pass
NFPA 285	Compliant with the 2006, 2009 & 2012 IBC for exterior walls of Type I, II, III and IV buildings of any height. See ICC-ES ESR 1172, Section 4.6 for specific assembly. Contact the Demilec USA Engineering Department for assistance with alternate assemblies.	Pass
ASTM E 970	SEALECTION® 500 may be left exposed on attic floors up to 14" thick.	Pass
ASTM E 119	Non load-bearing, 1 hour, wall assembly test. See ICC-ES ESR 1172, Section 4.5 for specific assembly. Contact the Demilec USA Engineering Department for assistance with alternate assemblies.	Pass
ASTM D 1929	Ignition properties (spontaneous ignition temperature)	1040°F (560°C)

Liquid Components Properties*		
Property	Isocyanate A-PMDI	SEALECTION® 500 Resin
Color	Brown	Amber
Viscosity @ 77°F (25°C)	180 – 220 cps	150 – 300 cps
Specific Gravity	1.24	1.08 – 1.12
Shelf Life of unopened drum properly stored	12 months	12 months
Storage Temperature	50 – 100°F (10 – 38°C)	50 – 100°F (10 – 38°C)
Mixing Ratio (volume)	1:1	1:1

*See MSDS for more information.

Reactivity Profile			
Cream time	Gel time	Tack free time	End of rise
1 – 2 seconds	3 – 4 seconds	6 – 7 seconds	6 – 7 seconds

Recommended Processing Conditions*		
Initial Primary Heater Setpoint Temperature	130°F	54°C
Initial Hose Heat Setpoint Temperature	130°F	54°C
Initial Processing Setpoint Pressure	1200 psi	8274 kPa
Substrate & Ambient Temperature	> 23°F	> -5°C
Moisture Content of Substrate	≤ 19 %	≤ 19 %
Moisture Content of Concrete	Concrete must be cured, dry and free of dust and form release agents.	

*Spray foam application temperatures and pressures can vary widely depending on temperature, humidity, elevation, substrate, equipment and other factors. While processing, the applicator must continuously observe the characteristics of the sprayed foam and adjust processing temperatures and pressures to maintain proper cell structure, adhesion, cohesion and general foam quality. It is the sole responsibility of the applicator to process and apply SEALECTION® 500 within specification.

General Requirements: Spray equipment must be capable of delivering the proper ratio (1:1 by volume) of polymeric isocyanate (PMDI) and polyol blend at adequate temperatures and spray pressures. Substrate must be at least 5 degrees above dew point, with best processing results when ambient humidity is below 80%. Substrate must also be free of moisture (dew or frost), grease, oil, solvents and other materials that would adversely affect adhesion of the polyurethane foam.

SEALECTION® 500 must be separated from the interior of the building by an approved thermal barrier or an approved finish material equivalent to a thermal barrier in accordance with applicable codes. SEALECTION® 500 must be sprayed at a minimum thickness of 3" per pass. This product must not be used when the continuous service temperature of the substrate or foam is below -60°F (-51°C) or above 180°F (82°C). SEALECTION® 500 should not be used in contact with bulk water, below grade or to cover flexible ductwork.

Disclaimer: The information herein is to assist customers in determining whether our products are suitable for their applications. We request that customers inspect and test our products before use and satisfy themselves as to contents and suitability. Nothing herein shall constitute a warranty, expressed or implied, including any warranty of merchantability or fitness, nor is protection from any law or patent inferred. All patent rights are reserved. The foam product is combustible and must be covered by an approved thermal barrier. Protect from direct flame and spark contact, around hot work for example. The exclusive remedy for all proven claims is replacement of our materials.

